PRIMER PER ADEPROOF VISTA

Primer for old bitumen membranes to be applied before ADEPROOF VISTA.





Technical data

PRIMER PER ADEPROOF VISTA is formulated for improving the adhesion on flexible liquid membranes on existing old bitumen membranes. This product is a primer based on synthetic resins in solvent, ready-foruse with high wetting capacity.

Applications

To be used on old bitumen membrane as adhesion primer before applying the product ADEPROOF VISTA.

Important warnings

- Do not apply at temperatures lower than +5°C or if rain is expected.
- Do not apply PRIMER PER ADEPROOF VISTA on wet substrates or subject to rising damp.
- Do not apply PRIMER PER ADEPROOF VISTA on loose and dusty substrates.

ADESITAL

- Do not apply PRIMER PER ADEPROOF VISTA on bitumen membranes that may still release oils or plasticizers.
- Do not apply PRIMER PER ADEPROOF VISTA on bitumen membranes with talc or that have been sanded.
- Do not dilute PRIMER PER ADEPROOF VISTA. The product is ready-for-use.
- PRIMER PER ADEPROOF VISTA is inflammable. Keep away from sparks and flames, do not smoke, avoid the build-up of electrostatic charges and work in well ventilated areas.
- PRIMER PER ADEPROOF VISTA is irritating to eyes, respiratory system and skin, may cause lung damage
 if swallowed. In case of contact with eyes or skin, rinse immediately with plenty of water and seek medical
 advice
- It is recommended to wear gloves and goggles and to adopt the standard precautions for handling chemicals.
- Wear a face mask with filter in case of insufficient ventilation. PRIMER PER ADEPROOF VISTA is hazardous to the aquatic environment. Avoid disposal of product in the environment.
- Do not apply PRIMER PER ADEPROOF VISTA on metal or painted substrates.
- Do not use on recently applied bitumen membranes (> 6 months); anyway, wait for the complete oxidation
 of the surface to be treated.

Substrate preparation

Bitumen membranes: Carefully clean the existing bitumen membrane until the substrate is clean and dry. The membrane must be intact, mechanically solid, perfectly clean and with no free water. Any detached or stiffened part must be locally removed and restored.

Product preparation

PRIMER PER ADEPROOF VISTA is a ready-for-use product. Open the package, briefly mix to make the consistency smooth and the product is ready for the application.

Product application

Carefully mix the product before the use until it is completely smooth. Apply a coat of PRIMER PER ADEPROOF VISTA on the clean and dry membrane using brush, roller or airless spraying (pumps type Taiver Gold 10.000 with 0.021" nozzle). Apply the waterproofing membrane ADEPROOF VISTA within 2 to 4 hours from the application of PRIMER PER ADEPROOF VISTA.

PRIMER PER ADEPROOF VISTA can be cleaned with solvent, like white spirit or nitro thinner.

Specifications

Liquid primer based on synthetic resins, e.g. PRIMER PER ADEPROOF VISTA by ADESITAL S.p.A., specific to improve the adhesion of flexible liquid membranes on existing bitumen membranes. The product must be applied at a temperature between +5°C and +35°C using brush, roller or airless spraying.

ADESITAL 2

Technical data (at +23°C and 50% R.H.) Appearance	Liquid
Colour	Transparent
Volume mass	0.96 g/cm ³
Solid residue	10%
Storage	24 months (in the original packaging and in a dr
Safety	Please check the information on the packag and on the Safety Sheet. PROTECT AGAINST FROST
Application data	
Application temperature	from +5°C to +35°C
Overlapping time	5 – 6 hours
Drying time	5 – 6 hours at +20°C
Coverage	0.20 kg/m² every coat
Packages PRIMER PER ADEPROOF VISTA	6 kg can (package approved according to ADI based on the Italian MD 22/02/1990)

Warning: The above indications and rules correspond to our best experience, but shall be deemed as merely indicative and shall be confirmed by exhaustive practical tests; thus, before using the product, the operator shall determine if it is suitable for its intended use and shall undertake every responsibility resulting from its use. PROFESSIONAL USE ONLY.

